



Vita-Crete®

Enriched Cement Mixes Since 1959

Typical Sieve Analysis

3/8" PEA GRAVEL (dry)
3/8" CRUSHED STONE (dry)

Sieve Analysis (% Passing by weight)

<u>Sieve Size</u>	<u>Typical Result</u>	<u>Specification</u>
1/2"	100%	100%
3/8"	93.4	85-100
#4	10.8	10-30
#8	1.1	0-10
#16	1.0	0-15

Customers and Users of **Vita-Crete®** Pea Gravel or Crushed Stone:

Pea Gravel is semi-round. Crushed stone is more angular.

Both are clean, dried and free of organic/deleterious materials.

Conforms to ASTM C-33 specifications for 3/8" aggregate.

The color is light beige, grey and pink but slight variations do occur.

If you need further specifications, please contact our office.

12 South Free Street • Building #4 • Milford, MA 01757 • Ph: 508-473-1799 • Fax: 508-473-1788